

| TECHNICAL FEATURES | |
|---|---------------------|
| Collection: Level marmi polished slabs Surface: Polished | Brand: Level |
| Size (cm): 160X320 | Thickness (mm): 6,5 |

Compliant with standard EN 14411:2016 annex G group Bla - GL

Compliant with standard ISO 13006:2018 annex G group Bla - GL

| Technical Features | Testing Method | Meas. unit | Average Typical Values | Established limits | | | |
|---|----------------|----------------------|-----------------------------|---|----------|---------|---------|
| DIMENSIONAL PROPERTIES AND SURFACE QUALITY | | | | | | | |
| Dimensions | | | | Nominal Length of edge N (cm) 7≤N<15 Nominal Length of edge N (cm) N≥15 | | | |
| Length and width (*) | ISO 10545-2 | (mm) (%) | Complies with the standards | ±2% (max 5mm) ±2% (max 5mm) ±2% (max 5mm) | | | |
| Length and width (**) | | | | | | | |
| Not Rectified | | | | ±0,9 mm | ±0,6% | ±2,0 mm | |
| Rectified | | | | ±0,4 mm | ±0,3 % | ±1,0 mm | |
| Thickness | | | | | | | |
| Not Rectified | | | | Complies with the standards | ±0,5 mm | ±5% | ±0,5 mm |
| Rectified | | | | | ±0,5 mm | ±5% | ±0,5 mm |
| Straightness of sides | | | | | | | |
| Not Rectified | | | | Complies with the standards | ±0,75 mm | ±0,5 % | ±1,5 mm |
| Rectified | | | | | ±0,4 mm | ±0,3 % | ±0,8 mm |
| Rectangularity | | | | | | | |
| Not Rectified | | | | Complies with the standards | ±0,75 mm | ±0,5% | ±2,0 mm |
| Rectified | | | | | ±0,4 mm | ±0,3% | ±1,5 mm |
| Surface Flatness c.c - e.c. - w. | | | | | | | |
| Not Rectified | | | | Complies with the standards | ±0,75 mm | ±0,5% | ±2,0 mm |
| Rectified | | | | | ±0,6 mm | ±0,4% | ±1,8 mm |
| Surface Quality | | | Complies with the standards | ≥95% | | | |
| PHYSICAL PROPERTIES | | | | | | | |
| Water absorption | ISO 10545-3 | (%) | ≤ 0,5 | Eb ≤ 0,5 (Individual maximum value 0,6%) | | | |
| Water absorption | ASTM C373-14 | (%) | ≤ 0,5 | | | | |
| Modulus of rupture | ISO 10545-4 | (N/mm ²) | ≥ 35 | R ≥ 35 (Individual minimum value 32 N/mm ²) | | | |
| Breaking Strength | ISO 10545-4 | (N) | ≥ 700 | ≥1300 (Thickness ≥7,5 mm) ≥700 (Thickness < 7,5 mm) | | | |
| Resistance to surface abrasion | ISO 10545-7 | | See attached table | Abrasion class and cycles passed | | | |
| Linear thermal expansion coefficient | ISO 10545-8 | (x(10)-6/°C) | ≤ 9 | Declared value (EN 14411:2016) Test Method available (ISO 13006:2018) | | | |
| Thermal shock resistance | ISO 10545-9 | | Complies with the standards | Declared value (EN 14411:2016) **** Test Method available (ISO 13006:2018) | | | |
| Crazing Resistance | ISO 10545-11 | | Complies with the standards | Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018) | | | |
| Frost resistance | ISO 10545-12 | | Complies with the standards | Pass according to EN ISO 10545-1 (EN 14411:2016) Required (ISO 13006:2018) | | | |
| Colour resistance to light exposure | DIN 51094 | | Complies with the standards | No sample must show noticeable colour modifications. | | | |

TECHNICAL FEATURES

| | |
|---|---------------------|
| Collection: Level marmi polished slabs Surface: Polished | Brand: Level |
| Size (cm): 160X320 | Thickness (mm): 6,5 |

| Technical Features | Testing Method | Meas. unit | Average Typical Values | Established limits |
|---|----------------|------------|------------------------|--|
| CHEMICAL PROPERTIES | | | | |
| Resistance to chemicals for household use and swimming pool salts | ISO 10545-13 | | A | GB Minimum (EN 14411:2016) GB Minimum (ISO 13006:2018) |
| Resistance to low concentrations of acids and alkalis | ISO 10545-13 | | LA | Declared value (EN 14411:2016) Test Method available (ISO 13006:2018) |
| Resistance to high concentrations of acids and alkalis | ISO 10545-13 | | HA | Declared value (EN 14411:2016) Test Method available (ISO 13006:2018) |
| Chemical Resistance | ASTM C650-04 | | Not Affected | Declared value (ANSI A137.1-2012) |
| Stain resistance | ISO 10545-14 | | Class 5 | Minimum class 3 (EN 14411:2016) Minimum class 3 (ISO 13006:2018) |

ANTISLIPPERY PROPERTIES

* The work size shall be chose, for non-modular tiles, so that the difference between the work size and the nominal size is:

** The deviation, in percent, of the average size for each tile (2 or 4 sides) from the work size..

**** See Table 2 for uses where it is applicable

c.c. Centre curvature, related to diagonal calculated from the work sizes

e.c. Edge curvature, related to the corresponding work sizes.

w. Warpage, related to diagonal calculated from the work sizes.

TECHNICAL FEATURES

| | |
|---|---------------------|
| Collection: Level marmi polished slabs Surface: Polished | Brand: Level |
| Size (cm): 160X320 | Thickness (mm): 6,5 |

| Resistance to surface | abrasion - ISO 10545-7 |
|------------------------------|---|
| Dark colors | Class 4 - Visible abrasion after 2100 cycles |
| Light colors | Class 5 - Visible abrasion after > 12000 cycles |